

AMENDMENTS TO THE CLAIMS

Claim 1 (Currently Amended) A foil-decorating sheet ~~comprised by~~ comprising a laminated film of two or more kinds of films which is to be set in an injection mold for being integrally bonded to a surface of a molding resin, wherein after a foil-decorating sheet is made, a bonding surface-side film of the laminated film which is on a side of a surface to be bonded to the molding resin has a peel strength of not less than 1 kgf / inch width at least at an interface between the molding resin and the bonding surface-side film of the laminated film bonded to the molding resin, and wherein at least a transparent acrylic film formed by extrusion which comprises ~~[[only]]~~ acrylic resin as its main component is laminated on the bonding surface-side film bonded to the molding resin, with a decorative layer formed between the acrylic film and the bonding surface-side film bonded to the molding resin.

A 1
Claim 2 (Currently Amended) A foil-decorating sheet ~~comprised by~~ comprising a laminated film of two or more kinds of films which is to be set in an injection mold for being integrally bonded to a surface of a molding resin, wherein after a foil-decorating sheet is made, a bonding surface-side film of the laminated film which is on a side of a surface to be bonded to the molding resin has a peel strength of not less than 1 kgf / inch width at least at an interface between the molding resin and the bonding surface-side film of the laminated film bonded to the molding resin, and wherein at least a transparent polycarbonate film which comprises polybutyleneterephthalate resin replaced with the acrylic resin is laminated on the bonding surface-side film bonded to the molding resin, with a decorative layer formed between the ~~[[acrylic]]~~ polycarbonate film and the bonding surface-side film bonded to the molding resin.

Claim 3 (Currently Amended) A foil-decorating sheet ~~comprised by~~ comprising a laminated film of two or more kinds of films which is to be set in an injection mold for being integrally bonded to a surface of a molding resin, wherein after a foil-decorating sheet is made, a bonding surface-side film of the laminated film which is on a side of a surface to be bonded to the molding resin has a peel strength of not less than 1 kgf / inch width at least at an interface between the molding resin and the bonding surface-side film of the laminated film bonded to the molding resin, and wherein at least a transparent acrylic film formed by extrusion is laminated on the bonding

surface-side film bonded to the molding resin, with a decorative layer formed between the acrylic film and the bonding surface-side film bonded to the molding resin, wherein when a tensile test is carried out with a test specimen, 80 mm wide, of the foil-decorating sheet held between a pair of chucks fixed at a distance of 100 mm between opposite chuck end edges of the chucks, by applying a load at constant rate of 100 mm / min to the test specimen at one end thereof under an ambient temperature condition of 110°C, the test specimen exhibits a tensile elongation at break of not less than 150%.

Claim 4 (Original) A foil-decorating sheet as defined in claim 3, wherein within a range of up to an upper limit of tensile elongation at break of the laminated film, constituent films of the laminated film have an applied load difference within a range of up to 5.0 kg maximum in their respective elongation values.

Claim 5 (Original) A foil-decorating sheet as defined in claim 3, wherein the sheet has a portion which is capable of being elongated more than 200% in unit area to preform a three-dimensional configuration.

Claim 6 (Original) A foil-decorating sheet as defined in claim 1, wherein the bonding surface-side film of the laminated film which is bonded to the molding resin is a polypropylene film.

Claim 7 (Original) A foil-decorating sheet as defined in claim 6, wherein the polypropylene film is formed of a noncrystalline or low-crystalline polypropylene resin having crystallinity of 50% or less.

Claim 8 (Currently Amended) A foil-decorating sheet as defined in claim 6, wherein the polypropylene film is comprised of a [[soft]] polypropylene resin polymerized by a metallocene catalyst.

Claim 9 (Original) A foil-decorating sheet as defined in claim 1, wherein the bonding surface-side film of the laminated film which is bonded to the molding resin is an acrylonitrile butadiene-styrene film.

Claim 10 (Original) A foil-decorating sheet as defined in claim 9, wherein a proportion a butadiene content in a copolymerization ratio of the acrylonitrile butadienestyrene film is 20 to 50% by weight.

Claim 11 (Currently Amended) A method of producing a foil-decorated resin molded article which comprises: three-dimensionally preforming the foil-decorating sheet as defined in claim 1; setting in the injection mold the three-dimensionally preformed foil-decorating sheet ~~as defined in claim 1~~; clamping the mold; injecting a molding resin mass in molten state into a cavity; and solidifying the molding resin to form a resin molded article and simultaneously therewith causing the foil-decorating sheet to go into integral bond with a surface of the resin molded article.

A (**Claim 12 (Original)** A method of producing a foil-decorated resin molded article which comprises: setting in the injection mold the foil-decorating sheet as defined in claim 1; preforming the sheet three-dimensionally within the mold; then clamping the mold; injecting a molding resin mass in molten state into a cavity; and solidifying the molding resin to form a resin molded article and simultaneously therewith, causing the foil-decorating sheet to go into integral bond with a surface of the resin molded article.
